



Features

- Strong adhesion to various substrates such as fabrics, metal, paper
- Excellent chemical resistance
- No VOC

Characteristic values

SKYBON Product	IV ⁽¹⁾ dl/g	Mn ⁽²⁾ Da	Tm °C	Tg ⁽³⁾ °C	MI g/10min, 2.16kg	Structure ⁽⁴⁾	Shape
EH-100	0.73	19,000	103	-7	37 @160°C	L	Pellet
EH-101	0.73	19,000	116	-1	29 @160°C	L	Pellet
EH-401	0.65	18,000	136	27	14 @160°C	L	Pellet
EH-500	0.63	17,000	170	21	39 @180°C	L	Pellet
EH-550	0.70	22,000	156	23	24 @180°C	L	Pellet
EH-575	0.66	18,000	170	22	27 @180°C	L	Pellet
EH-601	0.76	22,000	130	16	20 @175°C	L	Pellet
EH-601M	0.77	22,000	117	16	23 @175°C	L	Pellet
EH-700	0.61	27,000	101	14	40 @160°C	L	Pellet

(1) OSP at 35°C (2) THF (3) DSC (4) L : Linear

All data herein are believed to be correct. However, this should not be accepted as a guarantee of their accuracy and confirming tests should be run in your own plant or laboratory. and confirming tests should be run in your own plant or laboratory.