


WATER-BORNE POLYESTER RESIN



Features

- Outstanding water dispersibility
- Superior adhesion on general materials
- Amine-free / ammonia-free

Characteristic values

SKYBON Product	IV ⁽¹⁾ dl/g	Mn ⁽²⁾ Da	Tg ⁽³⁾ °C	OHV mgKOH/g	AV mgKOH/g	Dispersion ⁽⁴⁾ Media	Structure ⁽⁵⁾	Shape
EW-100Q	0.42	12,000	46	4	4	DW	L	Pellet
EW-100R	0.45	12,000	46	4	4	DW	L	Pellet
EW-210	0.35	12,000	60	5	3	DW	L	Pellet
EW-230	0.40	12,000	60	5	<3	DW/IPA	L	Pellet
EW-312	0.45	12,000	58	5	<3	DW/IPA	L	Pellet
EW-370	0.45	12,000	43	4	4	DW/IPA	L	Pellet

(1) OSP at 35°C (2) THF (3) DSC (4) DW : De-ionized Water (5) L : Linear

All data herein are believed to be correct. However, this should not be accepted as a guarantee of their accuracy and confirming tests should be run in your own plant or laboratory.