PRODUCT SPECIFICATIONS



STYLE RF-636T

DESCRIPTION: Tan Thermal Transfer Nonwoven Spun-bonded Polyester

SPECIFICATIONS:

Total Weight: 4.14 ± 0.30 oz./sq. yd. Total Thickness: 0.0066 ± 0.0010 in.

Opacity: >98%

Tear Strength (MD): 480 ± 100 grams Tear Strength (CD): 788 ± 200 grams Tensile Strength (MD): 130 ± 30 lbs. Tensile Strength (CD): 60 ± 15 lbs. Burst Strength: 64 ± 10 lbs.

GENERAL:

Coated with acrylic/urethane blend on both sides. Suited for conversion into permanent care labels. Meets Military Specifications DDD-L-20F and MIL-DTL-32075, as well as AATCC IVA wash test requirements. Exhibits excellent punching capabilities, excellent smoothness of hand, with good resistance to fadeout of imprinting from repeated commercial washings and dry cleaning. The product is non-fraying, resistant to shrinking and curling, and effectively resistant to degradation from rot, mildew and perspiration. Both surfaces are receptive to printing by most commonly used methods without shadow strikethrough.

This product is compliant with the Berry Amendment (USC, Title 10, Section 2533a) and the Kissel Amendment (H.R. 1)

Recommended

Printing Methods: Flexography., Hot Stamp and Thermal Transfer. Preference of printing

side (face) is indicated on product packaging.

ALL VALUES SHOWN ARE AVERAGE VALUES OBTAINED FROM COMMERCIAL PRODUCTION. THEY ARE INTENDED AS A GUIDE TO PRODUCT PROPERTIES AND NOT TO BE REGARDED AS SHIPPING SPECIFICATIONS.



Worthen Coated Fabrics Label Group Worthen Industries 1125 41st Street SE Grand Rapids, MI 49508

Tel: (616) 742-8990 Fax: (616) 742-8995 www.worthenindustries.com